

ISOFLEX-PU 560 BT

Two-component, polyurethane – bituminous, liquid waterproofing membrane

Description

Two-component, polyurethane – bituminous, liquid waterproofing membrane. ISOFLEX-PU 560 BT consists of hydrophobic polyurethane resins (component A) and bitumen (component B). The membrane formed is watertight, shows high elasticity and excellent mechanical and chemical resistance.

It offers the following advantages:

- A continuous, elastic, waterproof layer, without seams or joints.
- Excellent adhesion to various substrates, such as concrete, cement screeds, wood, bituminous coatings, steel surfaces.
- Applicability even to irregular substrates and in thick layers.
- Easy mixing (1:1 by volume).
- Quick-drying time.
- Crack-bridging ability.
- Joint-sealing solution.

Certified according to EN 1504-2 and classified as a coating for surface protection of concrete. CE marked.

Certificate No. 2032-CPR-10.11.

ISOFLEX-PU 560 BT is certified as root-resistant, according to UNE CEN/TS 14416 EX: 2014.

Fields of application

ISOFLEX-PU 560 BT is suitable for waterproofing:

- Underground constructions, e.g. foundations.
- Green roofs.
- Non-potable water tanks.
- Irrigation channels.
- Under tiles in kitchens, bathrooms, balconies, roofs and terraces, as long as quartz sand has been previously broadcast on its last layer.

- Under thermal insulation boards on terraces.
- In construction works, highways, tunnels, bridge decks, etc.

Technical data

1. Properties of the product in liquid form

Form:	mixture of polyurethane prepolymer resin and bitumen
Color:	black
Density (A+B):	1.00 kg/l
Mixing ratio:	1:1 by volume
Viscosity:	2,500 mPa·s (at +23°C)
Pot life:	40 min. (at +23°C)

2. Properties of the cured membrane

Elongation at break:	> 1,500%
(ASTM D 412)	
Tensile strength:	2 N/mm ²
(ASTM D412)	
Water impermeability:	5 atm
(DIN 1048)	
Adhesion:	> 2 N/mm ²
(EN 1542):	
Hardness:	30
(Shore A)	
Reaction to fire:	Euroclass F
(EN 13501-1)	
Service temperature:	from -40°C to +80°C

Directions for use

1. Substrate preparation

In general, the substrate must be dry (moisture content < 4%) and free of grease, loose particles, dust, etc.

ISOFLEX-PU 560 BT

1.1 Concrete substrates

Any existing cavities in concrete should be repaired in advance.

Severe cracks in the substrate must be locally primed and after 2-3 hours (depending on the weather conditions) must be sealed with the polyurethane sealants FLEX PU-30 S or FLEX PU-50 S.

Concrete and other porous surfaces should be treated with the polyurethane primer PRIMER-PU 100, at a consumption of approximately 200-300 g/m².

Surfaces with moisture content > 4% should be primed with the special two-component polyurethane primer PRIMER-PU 140, at a consumption of 100-200 g/m².

1.2 Smooth and non-absorbent substrates

Smooth and non-absorbent substrates, as well as bituminous membranes or old waterproofing layers, must be primed with the water-based epoxy primer EPOXYPRIMER 500, thinned with water up to 30% by weight. The product is applied by brush or roller in one coat.

Consumption: 150-200 g/m².

Depending on the weather conditions, ISOFLEX-PU 560 BT is applied within 24-48 hours from priming, as soon as the moisture content falls below 4%.

1.3 Metal surfaces

Metal surfaces should be:

- Dry and clean.
- Free of grease, loose particles, dust, etc. that may hinder adhesion.
- Free of rust or corrosion that may hinder adhesion.

Having been prepared by brushing, rubbing, sandblasting, etc., and then thoroughly cleaned from dust, metal surfaces are primed with the EPOXYCOAT-AC anticorrosive epoxy coating in 1 or 2 layers. EPOXYCOAT-AC is applied by roller, brush or spray. The second layer follows after the first has dried, but within 24 hours.

Consumption: 150-200 g/m²/layer.

Application of ISOFLEX-PU 560 BT should follow within the next 24-48 hours.

2. Application – Consumption

Components A (polyurethane resin) and B (bitumen) are packaged in different containers. Mix equal quantities of the two components into a clean container.

The two components are mixed for about 3 minutes with a low speed mixer (300 rpm). It is important to stir the mixture thoroughly near the walls and bottom of the container.

a) Total waterproofing of the surface

ISOFLEX-PU 560 BT is applied with a brush, roller or trowel 2-3 hours after priming and while PRIMER-PU 100 is still tacky.

Consumption: approx. 1.1-1.5 l/m², depending on the substrate.

b) Waterproofing under tiles

After applying ISOFLEX-PU 560 BT and while it is still fresh, quartz sand (Ø 0.3-0.8 mm) must be broadcast. The quartz sand must be completely dry.

Consumption of quartz sand: approx. 3 kg/m².

After 24 hours, any loose grains should be removed with a high suction vacuum cleaner.

When installing ceramic tiles, it is recommended to use high performance polymer-modified tile adhesives, such as ISOMAT AK 22, ISOMAT AK 25, ISOMAT AK-ELASTIC, ISOMAT AK-MEGARAPID.

Tools should be cleaned with SM-16 special solvent, while ISOFLEX-PU 560 BT is still fresh.

Packaging

10 l (A+B) and 40 l (A+B) containers.

ISOFLEX-PU 560 BT

Shelf life – Storage

12 months from production date if stored in original, unopened packaging at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

Remarks

- In case of application by spray, ISOFLEX-PU 560 BT may be diluted with a small quantity of SM-16 special solvent, depending on the weather conditions.
- ISOFLEX-PU 560 BT is not suitable for contact with chemically treated water of swimming pools.
- Temperature during application and hardening of the product should be between +8°C and +35°C.
- Containers that have been opened should be used at once and cannot be restored.
- ISOFLEX-PU 560 BT is intended for professional use only.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory j, type SB is 500 g/l (2010) for the ready-to-use product.

The ready-to-use product ISOFLEX-PU 560 BT contains a maximum of 500 g/l VOC.



2032

ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag Athanasios, Greece

16

2032-CPR-10.11B

DoP No.: ISOFLEX-PU 560 BT / 1841-01

EN 1504-2

Surface protection products

Coating

Permeability to CO₂: Sd > 50 m

Water vapor permeability: Class I (permeable)

Capillary absorption: w < 0.1 kg/m²·h^{0.5}

Adhesion: ≥ 0.8 N/mm²

Artificial weathering: Passes

Reaction to fire: Euroclass F

Dangerous substances comply with 5.3

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

MAIN OFFICES - FACTORY:

17th km Thessaloniki – Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: 22620 31 644

www.isomat.eu e-mail: info@isomat.eu

